

Softlines

<b>Test Report</b>	No. 28511291	Date: 17 <sup>th</sup> February 2021	Page 1 of 2
--------------------	--------------	--------------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:

<b>Sample Description</b>	:	Capture
<b>Customer</b>	:	Gabriel
<b>Colour</b>	:	4401
<b>Product type</b>	:	Upholstery fabric
<b>Fiber content</b>	:	-

Test Performed \* : Selected test(s) as requested by applicant \*  
 Sample Receiving Date : 11<sup>th</sup> January 2021  
 Testing Period : 11<sup>th</sup> January 2021 – 17<sup>th</sup> February 2021  
 Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property	Remarks
Dimensional Stability to Dry Cleaning	-
Abrasion	-
Abrasion Resistance ASTM D 4966	Sub-con within group results to follow on completion

Signed for and on behalf of  
TÜV Rheinland UK LTD



8400

*Test result is drawn according to the kind and extent of tests performed.  
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

**George Mehmet**  
Laboratory Technician



<b>Test Report</b>	No. 28511291	Date: 17 <sup>th</sup> February 2021	Page 2 of 2
--------------------	--------------	--------------------------------------	-------------

**Results:**

<b>Dimensional Change After Commercial Dry Cleaning</b> (Commercial dry clean cycle)	
<b>Direction</b>	<b>%Change</b>
Warp	0.0
Weft	0.0

<b>Abrasion Resistance</b> (BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)			
<b>Result</b>			
	<b>Specimen 1</b>	<b>Specimen 2</b>	<b>Specimen 3</b>
End point reached, No three thread breakdown	200,000	200,000	200,000
Overall result	200,000		
Colour Change At 3000 (rubs)	5	5	5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

-End of Test Report-