



Softlines

Test Report	No. 28515733	Date: 28 th March 2025	Page 1 of 3
-------------	--------------	-----------------------------------	-------------

AMENDMENT TEST REPORT

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description		:	V22 Downtown col 1107 Green
Customer		:	Gabriel; Hjulmagervej 55, DK, 9000 Aalborg
Submitted by		:	Alexander Holtermann
Style Number		:	V22 Downtown col 1107 Green
Colour		:	None Given
Product type		:	Upholstery
Fiber content		:	100% rec PES
Amendment to pilling resistance Test Performed	e grade	S :	Selected test(s) as requested by applicant
Sample Receiving Date Testing Period Test Result(s)	:		11 th March 2025 11 th March 2025 – 27 th March 2025 For further details, please refer to the following page(s).

Conclusion:

Test Property	Results
Abrasion Resistance	-
Pilling Resistance	-
Seam Slippage	-

* Sent to UK accredited UKAS Testing Centre

** Sent to in group Turkey accredited Testing Centre

Signed for and on behalf of TÜV Rheinland UK LTD

Christopher Clarke Digitally signed by Christopher Clarke Date: 2025.03.31 11:47:38 +01'00'



Chris Clarke Laboratory Supervisor

Test result is drawn according to the kind and extent of tests performed. Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.





Softlines

Test Report	No. 28515733	Date: 28 th March 2025	Page 2 of 3
-------------	--------------	-----------------------------------	-------------

Results:

		Result	
	Specimen 1	Specimen 2	Specimen 3
End point reached, three thread breakdown	120,000	120,000	120,000
Overall		120,000	
Colour Change At 3000 (rubs)	4-5	4-5	4-5

Pilling Resistance (BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric) No cleansing required		
Sample	Average Result	
After 2000 Rubs Rating	Fuzzing: 4-5 Pilling: 4-5 Matting: 4-5	
After 5000 Rubs Rating	Fuzzing: 4 Pilling: 4-5 Matting: 4-5	





Softlines

|--|

Seam Slippage (BS EN ISO 13936-2:2004)		
Sample	Result	
Warp	1.4 mm	
Weft	1.4 mm	

-End of Test Report-