

Applicant : Gabriel A/S China Office

Date : Nov 28, 2023

Attn : Anne Dong

Sample Description As Declared :


No. Of Sample : Five  
Fibre Content : -  
Material : Woven Fabric  
Finishing : -  
End Uses : -  
Colour : (A) 60213, (B) 60215, (C) 60217, (D) 61231, (E) 61236  
Style No. : London Curtain  
Order No./PO No. : 06969,06970,06971,06972,06973  
Buyer's Name : Gabriel  
Agent's Name : -  
Manufacturer's Name : -

Date Received/Date Test Started : Nov 13, 2023

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

Authorized By :  
For Intertek Testing Services  
(Tianjin) Ltd.



Patrick Gong  
General Manager

Tests Conducted:

1 Colour Fastness To Rubbing (ISO 105 X12-2016, Using The 16mm Diameter Rubbing Finger) :

Sample (A)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Sample (B)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Sample (C)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Sample (D)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Sample (E)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Tests Conducted:

Colour Fastness To Rubbing(Cont'd)

<u>Change in Colour</u>	<u>Warp</u>	<u>Weft</u>
Dry	4-5	4-5
Wet	4-5	4-5

2 Colour Fastness To Light (ISO 105 B02-2014, Method 2, Xenon-Arc Lamp) :

	(A)	(B)	(C)
Grade	5-6	6	5-6
	(D)	(E)	
Grade	6	6	

3 Fabric Propensity To Surface Pilling, Fuzzing Or Matting As Received (ISO 12945-2:2020, Martindale Abrasion & Pilling Tester, 415g Total Loading):

		<u>Mean Grade</u>	
<u>Sample (D)</u>	<u>Pilling</u>	<u>Fuzzing</u>	<u>Matting</u>
After 2,000 Revolutions	4-5	4-5	4-5
After 5,000 Revolutions	4-5	4-5	4-5

Remark : The Visual Assessment Of Pilling, Fuzzing And Matting Was Carried Out Respectively According To ISO 12945-4:2020.

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*