

Applicant : Gabriel A/S China Office
Rm 703, South Tower Soho Shangdu, No. 8 Dongdaqiao Road,
Chaoyang District, Beijing, 100020
Date : Jun 12, 2023
Attn : Anne Dong

Sample Description As Declared :


No. Of Sample : Thirteen
Fibre Content : 100% Polyester
Material : Woven Raising Fabric
Finishing : -
End Uses : -
Colour : (A) 61003 (B) 61159 (C) 61220 (D) 63035 (E) 65090 (F) 66164 (G) 66519
(H) 66520 (I) 67007 (J) 67039 (K) 68235 (L) 68509 (M) 68635
Style No. : Pesca
Order No./PO No. : -
Buyer's Name : Gabriel
Agent's Name : -
Manufacturer's Name : -

Date Received/Date Test Started : May 26, 2023

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.



Patrick Gong
General Manager

Tests Conducted:

1 Colour Fastness To Light (ISO 105 B02-2014, Method 2, Xenon-Arc Lamp) :

Grade	(A) 7	(B) 7	(C) 7	(D) 7
Grade	(E) 7	(F) 7	(G) 6-7	(H) 7
Grade	(I) 7	(J) 7	(K) 7	(L) 7
Grade	(M) 6-7			

2 Colour Fastness To Rubbing (ISO 105 X12-2016, Using The 16mm Diameter Rubbing Finger) :

Sample (A)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Sample (B)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Sample (C)

<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Change in Colour

	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Tests Conducted :

Colour Fastness To Rubbing(Cont'd)

Sample (D)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (E)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (F)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (G)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Tests Conducted :

Colour Fastness To Rubbing(Cont'd)

Sample (H)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (I)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (J)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (K)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

Tests Conducted :

Colour Fastness To Rubbing(Cont'd)

Sample (L)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>		
	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
Sample (M)		
<u>Staining</u>	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5
<u>Change in Colour</u>		
	Warp	Weft
Dry	4-5	4-5
Wet	4-5	4-5

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.