



Date of Issue: 1/29/2025
Report Number: 25-000197
Revision Number:1
Date Order Received: 01/23/2025

For the Account of: Gabriel A/S
Hjulmagervej 55
9000 Aalborg Denmark

Client's Identification: CURA LOOP COL. 68186

CERTIFICATE OF TESTING

TEST PERFORMED: Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D 5034-21(G-E)

TEST RESULTS

| | Specimen | Breaking Force lbf |
|------|----------|-----------------------|
| Warp | 1 | 217 |
| | 2 | 226 |
| | 3 | 214 |
| | 4 | 212 |
| | 5 | 219 |
| | Average | 218 |
| Fill | 1 | 249 |
| | 2 | 240 |
| | 3 | 244 |
| | 4 | 242 |
| | 5 | 246 |
| | 6 | 245 |
| | 7 | 224 |
| | 8 | 245 |
| | Average | 242 |

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received

ACCEPTANCE CRITERIA

| | |
|------------------------------|----------------------------|
| A.C.T. Standard | Acceptance Criteria |
| Upholstery | 50 pounds minimum |
| Panels and Upholstered Walls | 35 pounds minimum |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 01/27/2025