



Date of Issue: 4/8/2025
Report Number: 25-000837
Revision Number: 1
Date Order Received: 03/25/2025

For the Account of: Gabriel A/S
Hjulmagervej 55
9000 Aalborg Denmark

Client's Identification: 2379.2380 col. 2217

CERTIFICATE OF TESTING

TEST PERFORMED: Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)
1	213
2	213
3	220
4	208
5	216
Avg. Warp	214

	Breaking Force (lbf)
1	201
2	213
3	192
4	194
5	197
6	210
7	209
8	193
Avg. Fill	201

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received
Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Samples Tested: ☒Conditioned ☐After Wetting

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	50 pounds minimum
Panels and Upholstered Walls	35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 04/02/2025