

For the Account of

Gabriel A/S
Hjulgagervej 55
9000 Aalborg Denmark

Client's Identification

Morph col. 11102

CERTIFICATE OF TESTING

TEST PERFORMED Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics :
Martindale Tester ASTM D4970/D4970M-22

TEST RESULTS

Specimen	Rating
1	4.5
2	4.5
3	4.5
4	4.5
Average	4.5

RATING SYSTEM

Class 5.0	No Pilling
Class 4.0	Slight Pilling
Class 3.0	Moderate Pilling
Class 2.0	Severe Pilling
Class 1.0	Very Severe Pilling

NOTES

Test Conditions	70 ±4°F, 65 ±5% Relative Humidity
Sampling Method	As Received
Viewing Apparatus	SpectraLight QC Lightbooth
Viewing Option	45 degree
Rating Standard	ADJD3512 Photographic Standards
Running Times	1000 movements
Material Tested	As Received (no refurbishment), unless otherwise noted in Client Identification above

ACCEPTANCE CRITERIA

ACT Performance Guideline Criteria

	Woven + Knitted
Upholstery <i>Indoor</i>	Class 3.0, min
Upholstery <i>Outdoor</i>	Class 3.0, min

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 08/18/2026