

Applicant : Gabriel A/S China Office

Date : Oct 25, 2023

Attn : Anne Dong

Sample Description As Declared :


No. Of Sample : One
Fibre Content : -
Material : Woven Fabric
Finishing : -
End Uses : -
Colour : 60197
Style No. : Pesca
Order No./PO No. : -
Buyer's Name : Gabriel
Agent's Name : -
Manufacturer's Name : -

Date Received/Date Test Started : Oct 19, 2023

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.



Patrick Gong
General Manager

Tests Conducted:

1 Flammability Test (EN 1021-1 : 2014 Cigarette Test) :

The apparatus and method of testing were those described in EN 1021-1 : 2014 for upholstered furniture. Test carried out in assessing the ignitability of upholstered components when subjected to a smouldering cigarette. The test required the provided cover fabric to be tested with the provided filling.

Test Result : Non-Ignition

		Cigarette		
<u>Progressive Smouldering Failure</u>		1	2	3#
(A)	Test assembly displays escalating combustion behaviour	No	No	N/A
(B)	Test assembly that smoulders until it is largely consumed within the test duration	No	No	N/A
(C)	Test assembly smoulders to the extremities of the specimen, viz. upper or lower margins, either side or to its full thickness, within the duration of the test	No	No	N/A
(D)	Test assembly smoulders after one hour from the beginning of the test	No	No	N/A
(E)	On final examination progressive smouldering is observed	No	No	N/A
<u>Flaming Failure</u>				
(A)	Evidence of flaming in the interior and/or cover during combustion	No	No	N/A

Fabric / Filling	Time To Extinction After Placement Of Ignition Source			
	Flaming Ceased Time		Smoking Ceased Time	
	Min	Sec	Min	Sec
1	0	0	17	44
2	0	0	17	29
3#	-	-	-	-

Tests Conducted:

Flammability Test(Cont'd)

Remark : No = No, was not observed

N/A = Not applicable

= If one of two initial cigarettes fails to smoulder its complete length, repeat the test with the third cigarette.

Atmosphere for conditioning - The materials shall be conditioned for at least 24 hr in an atmosphere having a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 5\%$.

Note: The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; They are not intended as a means of assessing the full potential fire hazard of the materials in use.

The Sample Was Tested On Combination With Flame Retardant Conventional Polyurethane CMHR Foam Which Is Specified By The Client, Which Has A Density Of 35.0 Kg/M^3 . All Of These Were Requested By The Client.

Tests Conducted :

2 Flammability Test (EN 1021-2 : 2014 Match Test):

The apparatus and method of testing were those described in EN 1021-2 : 2014 for upholstered furniture. Test carried out in assessing the ignitability of upholstered components when subjected to a small flame as an ignition source. The test required the provided cover fabric to be tested with the provided filling.

Test Result : Non-Ignition

<u>Progressive Smouldering Failure</u>	<u>1st Test</u>	<u>2nd Test</u>	<u>3rd Test</u>
(A) Test assembly displays escalating combustion behaviour so that it is unsafe to continue the test and active extinction is necessary	No	No	No
(B) Test assembly that smoulders until it is largely consumed within the test duration	No	No	No
(C) Test assembly smoulders to the extremities of the specimen, viz. upper or lower margins, either side or to its full thickness, within the duration of the test	No	No	No
(D) Test assembly smoulders after one hour from the application of the ignition source	No	No	No
(E) On final examination progressive smouldering is observed	No	No	No
<u>Flaming Failure</u>	<u>1st Test</u>	<u>2nd Test</u>	<u>3rd Test</u>
(A) Test assembly displays escalating combustion behaviour so that it is unsafe to continue the test and active extinction is necessary	No	No	No
(B) Test assembly that burns until it is essentially consumed within test duration	No	No	No
(C) Test assembly on which any flame front reaches the lower margin, either side or passes through its full thickness within the duration of the test	No	No	No
(D) Any flaming which continues for more than 120 s after removal of the burner tube	No	No	No

Tests Conducted :

Flammability Test(Cont'd)

Fabric / Filling	Time To Extinction After Placement Of Ignition Source			
	Flaming Ceased Time		Smoking Ceased Time	
	Min	Sec	Min	Sec
1	0	30	0	51
2	0	21	0	42
3	0	37	0	55

Remark : N = No, was not observed

Atmosphere for conditioning - The materials shall be conditioned for at least 24 hr in an atmosphere having a temperature of $23\pm 2^{\circ}\text{C}$ and a relative humidity of $50\pm 5\%$.

Note: The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; They are not intended as a means of assessing the full potential fire hazard of the materials in use.

The Sample Was Tested On Combination With Flame Retardant Conventional Polyurethane CMHR Foam Which Is Specified By The Client, Which Has A Density Of 35.0 Kg/M^3 . All Of These Were Requested By The Client.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.