

TEST REPORT

2025AN3119

DATE OF RECEPTION

Date Format: dd/MM/yyyy 25/11/2025

DATE TESTS

Starting: 28/11/2025

Ending: 12/12/2025

APPLICANT

GABRIEL A/S
HJULMAGERVEJ, 55
DK-9000 Ålborg
Denmark

Att. BENTE ELLINGSOE

IDENTIFICATION AND DESCRIPTION OF SAMPLES

Reference by AITEX	Reference by customer	AITEX sample description
2025AN3119-S01	Shapeknit ARA Col.5099 Black	Tejido
2025AN3119-S02	Shapeknit ARA Col.5090 Dark Grey	Tejido
2025AN3119-S03	Shapeknit ARA Col.5018 Grey	Tejido
2025AN3119-S04	Shapeknit ARA Col.5017 Light Grey	Tejido
2025AN3119-S05	Shapeknit ARA Col.5110 Light Brown	Tejido
2025AN3119-S06	Shapeknit ARA Col.5333 Orange/Brown	Tejido
2025AN3119-S07	Shapeknit ARA Col.5432 Light Pink	Tejido
2025AN3119-S08	Shapeknit ARA Col.5113 Light Beige	Tejido
2025AN3119-S09	Shapeknit ARA Col.5460 Dark Red	Tejido
2025AN3119-S10	Shapeknit ARA Col.5690 Dark Blue	Tejido
2025AN3119-S11	Shapeknit ARA Col.5102 Beige	Tejido
2025AN3119-S12	Shapeknit ARA Col.5317 Orange	Tejido
2025AN3119-S13	Shapeknit ARA Col.5841 Dark Green	Tejido
2025AN3119-S14	Shapeknit ARA Col.5511 Red/Blue	Tejido
2025AN3119-S15	Shapeknit ARA Col.5715 Turquoise	Tejido
2025AN3119-S16	Shapeknit ARA Col.5828 Green	Tejido
2025AN3119-S17	Shapeknit ARA Col.5207 Light Yellow	Tejido
2025AN3119-S18	Shapeknit ARA Col.5237 Yellow	Tejido
2025AN3119-S19	Shapeknit ARA Col.5620 Blue/Yellow	Tejido
2025AN3119-S20	Shapeknit ARA Col.5614 Blue	Tejido
2025AN3119-S21	Shapeknit ARA Col.5320 Orange	Tejido
2025AN3119-S22	Shapeknit ARA Col.5616 Light Blue	Tejido
2025AN3119-S23	Shapeknit ARA Col.5327 Light Red	Tejido
2025AN3119-S24	Shapeknit ARA Col.5026 Grey	Tejido
2025AN3119-S25	Shapeknit Ara col. 5831 Light Green	Tejido
2025AN3119-S26	Shapeknit Ara col. 5122 Brown	Tejido
2025AN3119-S27	Shapeknit Ara col. 5101 Light Beige	Tejido
2025AN3119-S28	Shapeknit Ara col. 5430 Red	Tejido
2025AN3119-S29	Shapeknit Ara col. 5615 Blue	Tejido
2025AN3119-S30	Shapeknit Ara col. 5714 Light Turquoise	Tejido
2025AN3119-S31	Shapeknit Ara col. 5735 Dark Green	Tejido
2025AN3119-S32	Shapeknit Ara col. 5729 Turquoise	Tejido

Tests marked with * are not included within the scope of the ENAC accreditation.





2025AN3119-S33	Shapeknit Ara col. 5025 Grey	Tejido
2025AN3119-S34	Shapeknit Ara col. 5040 Light Grey	Tejido
2025AN3119-S35	Shapeknit Ara col. 5000 Ekru	Tejido
2025AN3119-S36	Shapeknit Aranat col.4604 Blue	Tejido
2025AN3119-S37	Shapeknit Aranat col.4001 Light Grey	Tejido
2025AN3119-S38	Shapeknit Aranat col.4022 Grey	Tejido
2025AN3119-S39	Shapeknit Aranat col.4099 Black	Tejido
2025AN3119-S40	Shapeknit Aranat col.4709 Turquoise	Tejido
2025AN3119-S41	Shapeknit Aranat col.4818 Dark Green	Tejido
2025AN3119-S42	Shapeknit Aranat col.4703 Dark Turquoise	Tejido
2025AN3119-S43	Shapeknit Aranat col.4602 Light Blue	Tejido
2025AN3119-S44	Shapeknit Aranat col.4610 Dark Blue	Tejido
2025AN3119-S45	Shapeknit Aranat col.4497 Pink	Tejido
2025AN3119-S46	Shapeknit Aranat col.4404 Red	Tejido
2025AN3119-S47	Shapeknit Aranat col.4420 Dark Red	Tejido
2025AN3119-S48	Shapeknit Aranat col.4102 Beige	Tejido
2025AN3119-S49	Shapeknit Aranat col.4220 Yellow	Tejido
2025AN3119-S50	Shapeknit Aranat col.4313 Orange	Tejido
2025AN3119-S51	Shapeknit Aranat col.4117 Dark Beige	Tejido
2025AN3119-S52	Shapeknit Aranat col.4104 Light Brown	Tejido
2025AN3119-S53	Shapeknit Aranat col.4810 Yellow/Blue	Tejido
2025AN3119-S54	Shapeknit Aranat col.4807 Light Green	Tejido

TESTS CARRIED OUT

- COLOUR FASTNESS TO ARTIFICIAL LIGHT.



RESULTS

COLOUR FASTNESS TO ARTIFICIAL LIGHT

Standard

EN ISO 105-B02:2014. Method 2

Apparatus

Xenotest ALPHA LM HIGH ENERGY 02364E06

Starting test date

28/11/2025

Ending test date

12/12/2025

Exposure conditions

Normal

Evaluation conditions

Light camera Gretagmacbeth (02021N06)

Reference	Light fastness
2025AN3119-S01	8
2025AN3119-S02	8
2025AN3119-S03	8
2025AN3119-S04	8
2025AN3119-S05	8
2025AN3119-S06	6
2025AN3119-S07	8
2025AN3119-S08	8
2025AN3119-S09	8
2025AN3119-S10	8
2025AN3119-S11	7-8
2025AN3119-S12	8
2025AN3119-S13	8
2025AN3119-S14	7-8
2025AN3119-S15	8
2025AN3119-S16	8
2025AN3119-S17	8
2025AN3119-S18	8
2025AN3119-S19	7-8
2025AN3119-S20	7
2025AN3119-S21	8
2025AN3119-S22	7-8
2025AN3119-S23	8
2025AN3119-S24	8
2025AN3119-S25	8
2025AN3119-S26	8
2025AN3119-S27	8
2025AN3119-S28	8
2025AN3119-S29	7-8
2025AN3119-S30	7-8
2025AN3119-S31	8
2025AN3119-S32	8
2025AN3119-S33	8
2025AN3119-S34	8
2025AN3119-S35	8
2025AN3119-S36	6



Reference	Light fastness
2025AN3119-S37	8
2025AN3119-S38	8
2025AN3119-S39	8
2025AN3119-S40	8
2025AN3119-S41	8
2025AN3119-S42	8
2025AN3119-S43	7-8
2025AN3119-S44	8
2025AN3119-S45	8
2025AN3119-S46	8
2025AN3119-S47	8
2025AN3119-S48	8
2025AN3119-S49	6-7
2025AN3119-S50	8
2025AN3119-S51	8
2025AN3119-S52	8
2025AN3119-S53	7-8
2025AN3119-S54	8

Remark

The fastness grade indicated comes up to:

- Depth change: More clear
- Hue change: No notes
- Brightness change: No notes

—————>>>

**MEANING OF COLOUR VALUES FASTNESS TO ARTIFICIAL LIGHT**

VALUE	MEANING
8	EXCELLENT
7	VERY GOOD
6	GOOD
5	MODERATE
4	FAIR
3	POOR BEHAVIOUR
2	POOR BEHAVIOUR
1	VERY POOR

//



Reference by AITEX	Description	Reference by customer
2025AN3119-S01	Shapeknit ARA Col.5099 Black	Shapeknit ARA Col.5099 Black
2025AN3119-S02	Shapeknit ARA Col.5090 Dark Grey	Shapeknit ARA Col.5090 Dark Grey
2025AN3119-S03	Shapeknit ARA Col.5018 Grey	Shapeknit ARA Col.5018 Grey
2025AN3119-S04	Shapeknit ARA Col.5017 Light Grey	Shapeknit ARA Col.5017 Light Grey
2025AN3119-S05	Shapeknit ARA Col.5110 Light Brown	Shapeknit ARA Col.5110 Light Brown
2025AN3119-S06	Shapeknit ARA Col.5333 Orange/Brown	Shapeknit ARA Col.5333 Orange/Brown
2025AN3119-S07	Shapeknit ARA Col.5432 Light Pink	Shapeknit ARA Col.5432 Light Pink
2025AN3119-S08	Shapeknit ARA Col.5113 Light Beige	Shapeknit ARA Col.5113 Light Beige
2025AN3119-S09	Shapeknit ARA Col.5460 Dark Red	Shapeknit ARA Col.5460 Dark Red
2025AN3119-S10	Shapeknit ARA Col.5690 Dark Blue	Shapeknit ARA Col.5690 Dark Blue
2025AN3119-S11	Shapeknit ARA Col.5102 Beige	Shapeknit ARA Col.5102 Beige
2025AN3119-S12	Shapeknit ARA Col.5317 Orange	Shapeknit ARA Col.5317 Orange
2025AN3119-S13	Shapeknit ARA Col.5841 Dark Green	Shapeknit ARA Col.5841 Dark Green
2025AN3119-S14	Shapeknit ARA Col.5511 Red/Blue	Shapeknit ARA Col.5511 Red/Blue
2025AN3119-S15	Shapeknit ARA Col.5715 Turquoise	Shapeknit ARA Col.5715 Turquoise
2025AN3119-S16	Shapeknit ARA Col.5828 Green	Shapeknit ARA Col.5828 Green
2025AN3119-S17	Shapeknit ARA Col.5207 Light Yellow	Shapeknit ARA Col.5207 Light Yellow
2025AN3119-S18	Shapeknit ARA Col.5237 Yellow	Shapeknit ARA Col.5237 Yellow
2025AN3119-S19	Shapeknit ARA Col.5620 Blue/Yellow	Shapeknit ARA Col.5620 Blue/Yellow
2025AN3119-S20	Shapeknit ARA Col.5614 Blue	Shapeknit ARA Col.5614 Blue
2025AN3119-S21	Shapeknit ARA Col.5320 Orange	Shapeknit ARA Col.5320 Orange
2025AN3119-S22	Shapeknit ARA Col.5616 Light Blue	Shapeknit ARA Col.5616 Light Blue
2025AN3119-S23	Shapeknit ARA Col.5327 Light Red	Shapeknit ARA Col.5327 Light Red
2025AN3119-S24	Shapeknit ARA Col.5026 Grey	Shapeknit ARA Col.5026 Grey
2025AN3119-S25	Shapeknit Ara col. 5831 Light Green	Shapeknit Ara col. 5831 Light Green
2025AN3119-S26	Shapeknit Ara col. 5122 Brown	Shapeknit Ara col. 5122 Brown
2025AN3119-S27	Shapeknit Ara col. 5101 Light Beige	Shapeknit Ara col. 5101 Light Beige
2025AN3119-S28	Shapeknit Ara col. 5430 Red	Shapeknit Ara col. 5430 Red
2025AN3119-S29	Shapeknit Ara col. 5615 Blue	Shapeknit Ara col. 5615 Blue
2025AN3119-S30	Shapeknit Ara col. 5714 Light Turquoise	Shapeknit Ara col. 5714 Light Turquoise
2025AN3119-S31	Shapeknit Ara col. 5735 Dark Green	Shapeknit Ara col. 5735 Dark Green
2025AN3119-S32	Shapeknit Ara col. 5729 Turquoise	Shapeknit Ara col. 5729 Turquoise
2025AN3119-S33	Shapeknit Ara col. 5025 Grey	Shapeknit Ara col. 5025 Grey
2025AN3119-S34	Shapeknit Ara col. 5040 Light Grey	Shapeknit Ara col. 5040 Light Grey
2025AN3119-S35	Shapeknit Ara col. 5000 Ekru	Shapeknit Ara col. 5000 Ekru
2025AN3119-S36	Shapeknit Aranats col.4604 Blue	Shapeknit Aranats col.4604 Blue
2025AN3119-S37	Shapeknit Aranats col.4001 Light Grey	Shapeknit Aranats col.4001 Light Grey
2025AN3119-S38	Shapeknit Aranats col.4022 Grey	Shapeknit Aranats col.4022 Grey
2025AN3119-S39	Shapeknit Aranats col.4099 Black	Shapeknit Aranats col.4099 Black



Reference by AITEX	Description	Reference by customer
2025AN3119-S40	Shapeknit Aranat col.4709 Turquoise	Shapeknit Aranat col.4709 Turquoise
2025AN3119-S41	Shapeknit Aranat col.4818 Dark Green	Shapeknit Aranat col.4818 Dark Green
2025AN3119-S42	Shapeknit Aranat col.4703 Dark Turquoise	Shapeknit Aranat col.4703 Dark Turquoise
2025AN3119-S43	Shapeknit Aranat col.4602 Light Blue	Shapeknit Aranat col.4602 Light Blue
2025AN3119-S44	Shapeknit Aranat col.4610 Dark Blue	Shapeknit Aranat col.4610 Dark Blue
2025AN3119-S45	Shapeknit Aranat col.4497 Pink	Shapeknit Aranat col.4497 Pink
2025AN3119-S46	Shapeknit Aranat col.4404 Red	Shapeknit Aranat col.4404 Red
2025AN3119-S47	Shapeknit Aranat col.4420 Dark Red	Shapeknit Aranat col.4420 Dark Red
2025AN3119-S48	Shapeknit Aranat col.4102 Beige	Shapeknit Aranat col.4102 Beige
2025AN3119-S49	Shapeknit Aranat col.4220 Yellow	Shapeknit Aranat col.4220 Yellow
2025AN3119-S50	Shapeknit Aranat col.4313 Orange	Shapeknit Aranat col.4313 Orange
2025AN3119-S51	Shapeknit Aranat col.4117 Dark Beige	Shapeknit Aranat col.4117 Dark Beige
2025AN3119-S52	Shapeknit Aranat col.4104 Light Brown	Shapeknit Aranat col.4104 Light Brown
2025AN3119-S53	Shapeknit Aranat col.4810 Yellow/Blue	Shapeknit Aranat col.4810 Yellow/Blue
2025AN3119-S54	Shapeknit Aranat col.4807 Light Green	Shapeknit Aranat col.4807 Light Green



RESULTS

COLOUR FASTNESS TO ARTIFICIAL LIGHT

Standard

AATCC TM 16.3:2020

Apparatus

Xenotest ALPHA LM HIGH ENERGY (02364E06)

Starting test date

09/12/2025

Ending test date

11/12/2025

Exposure conditions

Black Panel 63°C, Relative humidity 30%, 300-400 nm², 48W/m²

Total radiant energy

6912 KJ/m²

Test conditions

Without sample rotation, Mounting Procedure Backed.

Evaluation conditions

Light camera Gretagmacbeth (02021N06)

Grey Scale (0278N12)

>>>



Reference	Light fastness
2025AN3119-S01	5
2025AN3119-S02	5
2025AN3119-S03	5
2025AN3119-S04	5
2025AN3119-S05	5
2025AN3119-S06	5
2025AN3119-S07	5
2025AN3119-S08	5
2025AN3119-S09	5
2025AN3119-S10	5
2025AN3119-S11	5
2025AN3119-S12	5
2025AN3119-S13	5
2025AN3119-S14	5
2025AN3119-S15	5
2025AN3119-S16	5
2025AN3119-S17	5
2025AN3119-S18	5
2025AN3119-S19	5
2025AN3119-S20	5
2025AN3119-S21	5
2025AN3119-S22	5
2025AN3119-S23	5
2025AN3119-S24	5
2025AN3119-S25	5
2025AN3119-S26	5
2025AN3119-S27	5
2025AN3119-S28	5
2025AN3119-S29	5
2025AN3119-S30	5
2025AN3119-S31	5
2025AN3119-S32	5
2025AN3119-S33	5
2025AN3119-S34	5
2025AN3119-S35	5
2025AN3119-S36	5
2025AN3119-S37	5
2025AN3119-S38	5
2025AN3119-S39	5
2025AN3119-S40	5
2025AN3119-S41	5
2025AN3119-S42	5
2025AN3119-S43	5
2025AN3119-S44	5
2025AN3119-S45	5
2025AN3119-S46	5
2025AN3119-S47	5
2025AN3119-S48	5
2025AN3119-S49	5
2025AN3119-S50	5
2025AN3119-S51	5
2025AN3119-S52	5
2025AN3119-S53	5
2025AN3119-S54	5

Remark

The fastness grade indicated comes up to:
- Depth change: No notes



- Hue change: No notes
- Brightness change: No notes

MEANING OF COLOUR FASTNESS APPRAISAL EVALUATED WITH GREY SCALE

VALUE	MEANING
5	VERY GOOD- EXCELLENT
4	GOOD
3	FAIR - MODERATE
2	POOR BEHAVIOUR
1	VERY POOR

///



Reference by AITEX	Description	Reference by customer
2025AN3119-S01	Shapeknit ARA Col.5099 Black	Shapeknit ARA Col.5099 Black
2025AN3119-S02	Shapeknit ARA Col.5090 Dark Grey	Shapeknit ARA Col.5090 Dark Grey
2025AN3119-S03	Shapeknit ARA Col.5018 Grey	Shapeknit ARA Col.5018 Grey
2025AN3119-S04	Shapeknit ARA Col.5017 Light Grey	Shapeknit ARA Col.5017 Light Grey
2025AN3119-S05	Shapeknit ARA Col.5110 Light Brown	Shapeknit ARA Col.5110 Light Brown
2025AN3119-S06	Shapeknit ARA Col.5333 Orange/Brown	Shapeknit ARA Col.5333 Orange/Brown
2025AN3119-S07	Shapeknit ARA Col.5432 Light Pink	Shapeknit ARA Col.5432 Light Pink
2025AN3119-S08	Shapeknit ARA Col.5113 Light Beige	Shapeknit ARA Col.5113 Light Beige
2025AN3119-S09	Shapeknit ARA Col.5460 Dark Red	Shapeknit ARA Col.5460 Dark Red
2025AN3119-S10	Shapeknit ARA Col.5690 Dark Blue	Shapeknit ARA Col.5690 Dark Blue
2025AN3119-S11	Shapeknit ARA Col.5102 Beige	Shapeknit ARA Col.5102 Beige
2025AN3119-S12	Shapeknit ARA Col.5317 Orange	Shapeknit ARA Col.5317 Orange
2025AN3119-S13	Shapeknit ARA Col.5841 Dark Green	Shapeknit ARA Col.5841 Dark Green
2025AN3119-S14	Shapeknit ARA Col.5511 Red/Blue	Shapeknit ARA Col.5511 Red/Blue
2025AN3119-S15	Shapeknit ARA Col.5715 Turquoise	Shapeknit ARA Col.5715 Turquoise
2025AN3119-S16	Shapeknit ARA Col.5828 Green	Shapeknit ARA Col.5828 Green
2025AN3119-S17	Shapeknit ARA Col.5207 Light Yellow	Shapeknit ARA Col.5207 Light Yellow
2025AN3119-S18	Shapeknit ARA Col.5237 Yellow	Shapeknit ARA Col.5237 Yellow
2025AN3119-S19	Shapeknit ARA Col.5620 Blue/Yellow	Shapeknit ARA Col.5620 Blue/Yellow
2025AN3119-S20	Shapeknit ARA Col.5614 Blue	Shapeknit ARA Col.5614 Blue
2025AN3119-S21	Shapeknit ARA Col.5320 Orange	Shapeknit ARA Col.5320 Orange
2025AN3119-S22	Shapeknit ARA Col.5616 Light Blue	Shapeknit ARA Col.5616 Light Blue
2025AN3119-S23	Shapeknit ARA Col.5327 Light Red	Shapeknit ARA Col.5327 Light Red
2025AN3119-S24	Shapeknit ARA Col.5026 Grey	Shapeknit ARA Col.5026 Grey
2025AN3119-S25	Shapeknit Ara col. 5831 Light Green	Shapeknit Ara col. 5831 Light Green
2025AN3119-S26	Shapeknit Ara col. 5122 Brown	Shapeknit Ara col. 5122 Brown
2025AN3119-S27	Shapeknit Ara col. 5101 Light Beige	Shapeknit Ara col. 5101 Light Beige
2025AN3119-S28	Shapeknit Ara col. 5430 Red	Shapeknit Ara col. 5430 Red
2025AN3119-S29	Shapeknit Ara col. 5615 Blue	Shapeknit Ara col. 5615 Blue
2025AN3119-S30	Shapeknit Ara col. 5714 Light Turquoise	Shapeknit Ara col. 5714 Light Turquoise
2025AN3119-S31	Shapeknit Ara col. 5735 Dark Green	Shapeknit Ara col. 5735 Dark Green
2025AN3119-S32	Shapeknit Ara col. 5729 Turquoise	Shapeknit Ara col. 5729 Turquoise
2025AN3119-S33	Shapeknit Ara col. 5025 Grey	Shapeknit Ara col. 5025 Grey
2025AN3119-S34	Shapeknit Ara col. 5040 Light Grey	Shapeknit Ara col. 5040 Light Grey
2025AN3119-S35	Shapeknit Ara col. 5000 Ekru	Shapeknit Ara col. 5000 Ekru
2025AN3119-S36	Shapeknit Aranats col.4604 Blue	Shapeknit Aranats col.4604 Blue
2025AN3119-S37	Shapeknit Aranats col.4001 Light Grey	Shapeknit Aranats col.4001 Light Grey
2025AN3119-S38	Shapeknit Aranats col.4022 Grey	Shapeknit Aranats col.4022 Grey
2025AN3119-S39	Shapeknit Aranats col.4099 Black	Shapeknit Aranats col.4099 Black



Reference by AITEX	Description	Reference by customer
2025AN3119-S40	Shapeknit Aranat col.4709 Turquoise	Shapeknit Aranat col.4709 Turquoise
2025AN3119-S41	Shapeknit Aranat col.4818 Dark Green	Shapeknit Aranat col.4818 Dark Green
2025AN3119-S42	Shapeknit Aranat col.4703 Dark Turquoise	Shapeknit Aranat col.4703 Dark Turquoise
2025AN3119-S43	Shapeknit Aranat col.4602 Light Blue	Shapeknit Aranat col.4602 Light Blue
2025AN3119-S44	Shapeknit Aranat col.4610 Dark Blue	Shapeknit Aranat col.4610 Dark Blue
2025AN3119-S45	Shapeknit Aranat col.4497 Pink	Shapeknit Aranat col.4497 Pink
2025AN3119-S46	Shapeknit Aranat col.4404 Red	Shapeknit Aranat col.4404 Red
2025AN3119-S47	Shapeknit Aranat col.4420 Dark Red	Shapeknit Aranat col.4420 Dark Red
2025AN3119-S48	Shapeknit Aranat col.4102 Beige	Shapeknit Aranat col.4102 Beige
2025AN3119-S49	Shapeknit Aranat col.4220 Yellow	Shapeknit Aranat col.4220 Yellow
2025AN3119-S50	Shapeknit Aranat col.4313 Orange	Shapeknit Aranat col.4313 Orange
2025AN3119-S51	Shapeknit Aranat col.4117 Dark Beige	Shapeknit Aranat col.4117 Dark Beige
2025AN3119-S52	Shapeknit Aranat col.4104 Light Brown	Shapeknit Aranat col.4104 Light Brown
2025AN3119-S53	Shapeknit Aranat col.4810 Yellow/Blue	Shapeknit Aranat col.4810 Yellow/Blue
2025AN3119-S54	Shapeknit Aranat col.4807 Light Green	Shapeknit Aranat col.4807 Light Green

**MEANING OF COLOUR FASTNESS APPRAISAL EVALUATED WITH GREY SCALE**

VALUE	MEANING
5	VERY GOOD - EXCELLENT
4	GOOD
3	FAIR - MODERATE
2	POOR - BEHAVIOUR
1	VERY POOR

According to standards ISO 105-A02 e ISO 105-A03



Isabel Soriano
Laboratories and International Offices Subdirector



Date: 16/12/2025 7:26:50

Digitally Signed by: MARIA ISABEL SORIANO SARRIO -

NIF: 52716426N

LIABILITY CLAUSES

- 1.- AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2.- AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document. AITEX laboratories do not carry out sampling.
- 3.- The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4.- In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5.- AITEX will provide at the request of the person concerned, the treatment of complaints procedure. In the event that you want to make it, direct it to: calidad@aitex.es.
- 6.- AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results.
- 7.- AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8.- AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9.- When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule according to ILAC-G8: 2009 will be applied with a security zone of 1U and a Probability of False Acceptance <2.5%.
- 10.- The uncertainties of tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (95% probability of coverage). If not informed, they are available to the client in AITEX.
- 11.- The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 12.- This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13.- The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14.- The client must attend at all times, to the dates of the realization of the tests.
- 15.- According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16.- This report may not be partially reproduced without the written approval of the issuing laboratory.