

Softlines

Test Report	No. 28511296	Date: 5 th March 2021	Page 1 of 2
--------------------	--------------	----------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:


Sample Description	:	Runner
Customer	:	Gabriel
Colour	:	60011
Product type	:	Upholstery fabric
Fiber content	:	-

Test Performed * : Selected test(s) as requested by applicant *
 Sample Receiving Date : 11th January 2021
 Testing Period : 11th January 2021 – 5th March 2021
 Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Results
Colour fastness to Washing	-
Colour fastness to Perspiration	-
Colour fastness to Water Spotting	Sub con to third party
Colour fastness to Rubbing (Organic Solvents)	Sub-con within group results to follow on completion
Abrasion (ASTM D 4157)	Sub-con within group results to follow on completion

Signed for and on behalf of
TÜV Rheinland UK LTD

 George Mehmet
2021.03.05
12:59:32 Z

George Mehmet
Laboratory Technician



8400

*Test result is drawn according to the kind and extent of tests performed.
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*



Test Report	No. 28511296	Date: 5 th March 2021	Page 2 of 2
--------------------	--------------	----------------------------------	-------------

Results:

Colour Fastness To Washing (BS EN ISO 105-C06: 2010) Washing Condition: A2S, 40°C With ECE(B) + Sodium Perborate, 10 Steel Balls.	
Sample	Result
Colour Change	5
Self-Staining	-
Colour Staining	Result
Acetate	5
Cotton	5
Polyamide	5
Polyester	5
Acrylic	5
Wool	5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

Colour Fastness To Perspiration (BS EN ISO 105-E04: 2013)		
Sample	Result	
	Acid	Alkaline
Colour Change	5	5
Self-Staining	-	-
Colour Staining	Result	Result
Acetate	5	5
Cotton	5	5
Polyamide	5	5
Polyester	5	5
Acrylic	5	5
Wool	5	5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good		

Colour Fastness To Water spotting (BS EN ISO 105-E16:2007)	
	Result
Shade change centre	5
Shade change periphery	5

-End of Test Report-