



Date of Issue: 6/4/2025  
Report Number: 25-001496  
Revision Number: 1  
Date Order Received: 05/30/2025

For the Account of: Gabriel A/S  
Hjulmagervej 55  
9000 Aalborg Denmark

Client's Identification: NOMA

## CERTIFICATE OF TESTING

**TEST PERFORMED:** Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics :  
Brush Pilling Tester ASTM D3511/D3511M-16(2022)

### TEST RESULTS

	Rating
Left	5.0
Center	5.0
Right	5.0
Average Rating	5.0

### RATING SYSTEM

Class 5.0	No Pilling
Class 4.0	Slight Pilling
Class 3.0	Moderate Pilling
Class 2.0	Severe Pilling
Class 1.0	Very Severe Pilling

### NOTES

<b>Test Conditions:</b>	70 ±4°F, 65 ±5% Relative Humidity
<b>Sampling Method:</b>	As Received
<b>Viewing Apparatus:</b>	Macbeth Lightbooth
<b>Viewing Option:</b>	45 degree
<b>Rating Standard:</b>	ADJD3512 Photographic Standards
<b>Running Times:</b>	4 minutes brushing / 2 minutes pilling
<b>Material Tested:</b>	As Received (no refurbishment), unless otherwise noted in Client Identification above

### ACCEPTANCE CRITERIA

<b>A.C.T. Standard:</b>	<b>Acceptance Criteria</b>
Upholstery	Class 3 minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 06/03/2025