

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark.accounting@sgs.com

Page 1

Received: 10/26	6/2018 Completed: 11/08/2018	Letter: Z5	RV	P.O.#:	Test Report #:	3-2	9270-5-
Client's Identification	Style: Spin. Content: 100% Tre Upholstery.	vira CS. Finish:	None.	Weight: 407 g/lm. Col	or: 61149 Light Brown.	Product End 1	Use:
	ente Ellingsoe, Quality Dep abriel A/S	artment		Key Test:	ASTM D 4034/ACT		150
	julmagervej 55 K-9000 Aalborg, Denmark				011-45-9630-3100 011-45-9811-6125	Ext:	
			and the second state			CONTRACTOR NAMED IN CONTRACTOR	

Test Category: Seam Slippage

Specifier: ACT

LE 2015; V 08/15 PC: 8H

dl/SM

NTR 6/16

TEST PERFORMED: ASTM D 4034 - Standard Test Method for Resistance to Yarn Slippage at the Sewn Seam in Woven Upholstery Fabrics - Plain, Tufted, or Flocked --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery

ACCEPTANCE CRITERIA: 25 lbf minimum average for warp and weft

SEAM CONSTRUCTION:

Seam Allowance: 0.5"

Seam Type:

301 Lockstitch

Thread Type:

100% Nylon Bonded Monocord;

Needle Thread size 8/Bobbin Thread Size 5

Needle:

Size 22 Ball Point

Stitches/Inch: 7 ± 0.5

RESULTS: Specimen results reported to the nearest 0.5 lb force (lbf)

Average reported to the nearest 0.5 lb force (lbf)

	Specimen #	(lbf)
Warp Yarn Slippage:	1	92.0 SB
(seamed in warp direction)	2	97.5 SB
	3	84.5 SB
	4	94.0 SB
	5	87.0 SB
	Avg	: 91.0
Weft Yarn Slippage:	6	96.5 FBS
(seamed in weft direction)	7	97.5 FBS
	8	107.5 FBS
	9	98.5 FBS
	10	106.5 FBS
	Avg	: 101.0

ABBREVIATIONS WHICH MAY BE USED:

SS = Seam Slippage

SB = Seam break before 1/4" slippage

FB = Fabric break before 1/4" slippage

FBS = Fabric break at Seam before 1/4" slippage

(Page 1 of 2)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark.accounting@sgs.com

Page 2

Received: 10/26/2018 Completed: 11/08/2018 Letter: Z5	RV P.O.#: Test Report #:	3-29270-5-
Client's Style: Spin. Content: 100% Trevira CS. Finish: No Upholstery.	ne. Weight: 407 g/lm. Color: 61149 Light Brown.	. Product End Use:
Tested For: Bente Ellingsoe, Quality Department Gabriel A/S	Key Test: ASTM D 4034/ACT	150
Hjulmagervej 55 DK-9000 Aalborg, Denmark	Tel: 011-45-9630-3100 Fax: 011-45-9811-6125	Ext:

REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [] Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE

sgs govmark /gb /jab Phyllis Pettit

NOV 2 8 2018

(Page 2 of 2)