



Confidential Report

Our Ref: 23/60815A-Supp/03/23





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 12 December 2024

Our Ref: 23/60815A-sup/03/23
Your Ref: ---

Page: 1 of 4

Client:

Gabriel A/S

Hjulgagerve 55
DK-900 Aalborg
Denmark

Job Title:

Fire Test on One Fabric Sample

Clients Order Ref:

--

Date of Receipt:

23 March 2023

Date Test Started:

5 April 2023

Description of Sample:

One sample of fabric, which was referenced by the client as;

Focus Melange - FR, Colour number - 64242

This is a supplementary report to the one issued on the 13th April 2024 under our report reference 23/60815A/03/23

Work Requested:

We were asked to make the following fire test:

BS 5852: Clause 11:2006 (2011)

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 12 December 2024

Our Ref: 23/60815A-sup/03/23
Your Ref: ---

Page: 2 of 4

Client: Gabriel A/S

Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)

Pre-Treatment

The material was subjected to the water soak procedure according to BS 5852:Annex E:2006 (2011).

Conditioning

The sample was conditioned and tested in the environments specified in Clause 10 of BS 5852: 2006 (2011).

Testing

The material was tested according to BS 5852:2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 18°C and 50% relative humidity (R.H.).

The sample was tested over combustion modified polyurethane foam with a density of approximately 35kg/m³.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: info@bttg.co.uk
 : www.bttg.co.uk

Date: 12 December 2024

Our Ref: 23/60815A-sup/03/23
 Your Ref: ---

Page: 3 of 4

Client: **Gabriel A/S**

Results

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1	Specimen 2
Time of Ignition (min/secs)	24	23
Time of Flame Extinction (min/secs)	5.26	4.35
Time of Smoke Extinction (min/secs)	6.44	6.24
Time of cover split (min/secs)	DNS	DNS
Extent of damage (mm) - Seat		
Width	82	81
Length	67	67
Depth	34	29
Extent of damage (mm) - Back		
Width	81	81
Depth	34	26
Melting	No	No
Dripping	No	No
Charring	Yes	Yes
Comments and Observations	DNS	DNS
Specimen Result (Ignition or Non-ignition)	Non-Ignition	Non-Ignition

Acronyms

ME – Manually extinguished
 DNO – Did not observe time of events

EC – Escalating combustion
 BTT – Burnt through thickness of foam

DNS – Material did not split
 BTE – Burnt to extremities





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 12 December 2024

Our Ref: 23/60815A-sup/03/23
Your Ref: ---

Page: 4 of 4

Client: Gabriel A/S

Comment

The results indicate 'Non-Ignition' of the materials and the test is designated NI/5 (ie. Pass).

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (<http://www.bttg.co.uk/decision-rules-policy>) for further information.

Uncertainty Budget

Measurements: ± 2 mm

Timings: ± 2 seconds

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.