

TEST REPORT

2025AN0934

DATE OF RECEPTION

Date Format: dd/MM/yyyy 06/05/2025

DATE TESTS

Starting: 12/05/2025

Ending: 26/05/2025

APPLICANT

GABRIEL A/S
HJULMAGERVEJ, 55
DK-9000 Ålborg
Denmark

Att. BENTE ELLINGSOE

IDENTIFICATION AND DESCRIPTION OF SAMPLES

Reference by AITEX	Reference by customer		AITEX sample description
2025AN0934-S01	Design nr.2380	2201 Black	Fabric
2025AN0934-S02	Design nr.2380	2202 Light grey	Fabric
2025AN0934-S03	Design nr.2380	2213 Light Beige	Fabric
2025AN0934-S04	Design nr.2380	2214 Dark brown	Fabric
2025AN0934-S05	Design nr.2380	2215 Orange	Fabric
2025AN0934-S06	Design nr.2380	2216 Yellow green	Fabric
2025AN0934-S07	Design nr.2380	2217 Yellow Green	Fabric
2025AN0934-S08	Design nr.2380	2218 Yellow beige	Fabric
2025AN0934-S09	Design nr.2380	2219 Orange beige	Fabric
2025AN0934-S10	Design nr.2380	2220 Dark orange	Fabric
2025AN0934-S11	Design nr.2380	2221 Blue	Fabric
2025AN0934-S12	Design nr.2380	2222 Dark blue	Fabric

TESTS CARRIED OUT

- COLOUR FASTNESS TO RUBBING.

Tests marked with * are not included within the scope of the ENAC accreditation.





RESULTS

COLOUR FASTNESS TO RUBBING

Standard

ISO 105-X12:2016

Apparatus

Crockmeter

Starting test date

12/05/2025

Ending test date

26/05/2025

Conditioning time

> 4 H

Atmosphere for conditioning and testing

Temperature	(20±2) °C
Relative Humidity	(65±2) %Hr

Pin

Cylindrical

Applied force

(9 ± 0,2) N

% of water absorption for rubbing in humid

95-100 %



REFERENCE	DIRECTION	DRY STAINING	WET STAINING
2025AN0934-S01	Warp	4-5	4-5
	Weft	4-5	4-5
2025AN0934-S02	Warp	5	5
	Weft	5	5
2025AN0934-S03	Warp	5	5
	Weft	5	5
2025AN0934-S04	Warp	5	5
	Weft	5	5
2025AN0934-S05	Warp	4-5	4-5
	Weft	4-5	4-5
2025AN0934-S06	Warp	4-5	4-5
	Weft	4-5	4-5
2025AN0934-S07	Warp	5	5
	Weft	5	5
2025AN0934-S08	Warp	5	5
	Weft	5	5
2025AN0934-S09	Warp	5	5
	Weft	5	5
2025AN0934-S10	Warp	4-5	4-5
	Weft	4-5	4-5
2025AN0934-S11	Warp	5	5
	Weft	5	5
2025AN0934-S12	Warp	5	5
	Weft	5	5

>>>



REFERENCE	DIRECTION	CHANGUE IN COLOUR DRY	CHANGUE IN COLOUR WET
2025AN0934-S01	Warp	5	5
	Weft	5	5
2025AN0934-S02	Warp	5	5
	Weft	5	5
2025AN0934-S03	Warp	5	5
	Weft	5	5
2025AN0934-S04	Warp	5	5
	Weft	5	5
2025AN0934-S05	Warp	5	5
	Weft	5	5
2025AN0934-S06	Warp	5	5
	Weft	5	5
2025AN0934-S07	Warp	5	5
	Weft	5	5
2025AN0934-S08	Warp	5	5
	Weft	5	5
2025AN0934-S09	Warp	5	5
	Weft	5	5
2025AN0934-S10	Warp	5	5
	Weft	5	5
2025AN0934-S11	Warp	5	5
	Weft	5	5
2025AN0934-S12	Warp	5	5
	Weft	5	5

///



Reference by AITEX	Description	Reference by customer
2025AN0934-S01	Fabric	Design nr.2380 2201 Black
2025AN0934-S02	Fabric	Design nr.2380 2202 Light grey
2025AN0934-S03	Fabric	Design nr.2380 2213 Light Beige
2025AN0934-S04	Fabric	Design nr.2380 2214 Dark brown
2025AN0934-S05	Fabric	Design nr.2380 2215 Orange
2025AN0934-S06	Fabric	Design nr.2380 2216 Yellow green
2025AN0934-S07	Fabric	Design nr.2380 2217 Yellow Green
2025AN0934-S08	Fabric	Design nr.2380 2218 Yellow beige
2025AN0934-S09	Fabric	Design nr.2380 2219 Orange beige
2025AN0934-S10	Fabric	Design nr.2380 2220 Dark orange
2025AN0934-S11	Fabric	Design nr.2380 2221 Blue
2025AN0934-S12	Fabric	Design nr.2380 2222 Dark blue



RESULTS

COLOUR FASTNESS TO RUBBING

Standard

AATCC TM 8:2016

Apparatus

Crockmeter

Starting test date

12/05/2025

Ending test date

22/05/2025

Scale used

AATCC Gray scale for staining (AATCC evaluation procedure 2)

Reference	Dry staining	Wet staining
2025AN0934-S01	5	5
2025AN0934-S02	5	5
2025AN0934-S03	4-5	4-5
2025AN0934-S04	4-5	4-5
2025AN0934-S05	5	4-5
2025AN0934-S06	5	5
2025AN0934-S07	5	5
2025AN0934-S08	5	5
2025AN0934-S09	5	5
2025AN0934-S10	4-5	4-5
2025AN0934-S11	5	4-5
2025AN0934-S12	5	4-5

///

Reference by AITEX	Description	Reference by customer
2025AN0934-S01	Fabric	Design nr.2380 2201 Black
2025AN0934-S02	Fabric	Design nr.2380 2202 Light grey
2025AN0934-S03	Fabric	Design nr.2380 2213 Light Beige
2025AN0934-S04	Fabric	Design nr.2380 2214 Dark brown
2025AN0934-S05	Fabric	Design nr.2380 2215 Orange
2025AN0934-S06	Fabric	Design nr.2380 2216 Yellow green
2025AN0934-S07	Fabric	Design nr.2380 2217 Yellow Green
2025AN0934-S08	Fabric	Design nr.2380 2218 Yellow beige
2025AN0934-S09	Fabric	Design nr.2380 2219 Orange beige
2025AN0934-S10	Fabric	Design nr.2380 2220 Dark orange
2025AN0934-S11	Fabric	Design nr.2380 2221 Blue
2025AN0934-S12	Fabric	Design nr.2380 2222 Dark blue

**MEANING OF COLOUR FASTNESS APPRAISAL EVALUATED WITH GREY SCALE**

VALUE	MEANING
5	VERY GOOD - EXCELLENT
4	GOOD
3	FAIR - MODERATE
2	POOR - BEHAVIOUR
1	VERY POOR

According to standards ISO 105-A02 e ISO 105-A03



Isabel Soriano
Laboratories and International Offices Subdirector



Date: 27/05/2025 15:54:22

Digitally Signed by: MARIA ISABEL SORIANO SARRIO -

NIF:52716426N

LIABILITY CLAUSES

- 1.- AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2.- AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document. AITEX laboratories do not carry out sampling.
- 3.- The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4.- In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5.- AITEX will provide at the request of the person concerned, the treatment of complaints procedure. In the event that you want to make it, direct it to: calidad@aitex.es.
- 6.- AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results. The information provided by the client is not covered by the scope of ENAC accreditation.
- 7.- AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8.- AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9.- When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule according to ILAC-G8: 2009 will be applied with a security zone of 1U and a Probability of False Acceptance <2.5%.
- 10.- The uncertainties of tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (95% probability of coverage). If not informed, they are available to the client in AITEX.
- 11.- The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 12.- This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13.- The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14.- The client must attend at all times, to the dates of the realization of the tests.
- 15.- According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16.- This report may not be partially reproduced without the written approval of the issuing laboratory.