



For the Account of Gabriel A/S
Hjulmagervej 55
9000 Aalborg Denmark

Client's Identification SAIL col. 70999

CERTIFICATE OF TESTING

TEST PERFORMED Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-21(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)
1	287
2	284
3	259
4	282
5	305
Avg. Warp	283

	Breaking Force (lbf)
1	250
2	238
3	243
4	269
5	249
6	257
7	244
8	225
Avg. Fill	247

NOTES

Test Conditions 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method As Received
Equipment Used Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum 1000 pounds
Jaw Size 1 inch x 1 inch (face and back), rubber coated
Samples Tested Conditioned After Wetting

ACCEPTANCE CRITERIA

ACT Performance Guideline Criteria

Woven + Knitted
Upholstery, *Indoor + Outdoor* 50 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 11/24/2025