



NUMBER : TSNT00525781

Applicant : Gabriel A/S China Office
Rm 703, South Tower Soho Shangdu, No. 8 Dongdaqiao Road,
Chaoyang District, Beijing, 100020
Attn : Anne Dong

Date : Apr 19, 2013

Sample Description:

Five (5) Pieces Of Submitted Cutting Said To Be 100% Polyester Woven Fabric In (A) 68097 Green, (B) 61159 Light Beige, (C) 61160 Dark Beige, (D) 60137 Light Grey, (E) 60138 Dark Grey For Contract.

Date Received : 04/10/2013
Date Tests Started : 04/10/2013
Style No. : SODLEY

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.

Alex Wang
General Manager



NUMBER : TSNT00525781

Tests Conducted:

1. Colour Fastness To Rubbing (ISO 105 X12-2001, Using The 16mm Diameter Rubbing Finger) :

	(A)	(B)	(C)	(D)	(E)
Dry	4-5	4-5	4-5	4-5	4-5
Wet	4-5	4-5	4-5	4-5	4-5

2. Colour Fastness To Light (ISO/105 B02-1994, Xenon-Arc Lamp, Method 3) :

	(A)	(B)	(C)	(D)	(E)
Up To GR 5 Grade	4	4-5	4-5	4-5	4

3. Seam Resistance As Received (ISO 13936-2:2004, Instron, CRE) :

Sample(A)

The Mean Seam Opening Under 180 N

// To Warp	2.0 mm.
// To Weft	2.0 mm.

4. Pilling Resistance Before Wash (ISO 12945-2-2000, Modified Martindale Method) :

Sample(A)

After A 2000-Cycle Test

Rating 4

After A 5000-Cycle Test

Rating 4

5. Abrasion Resistance (ISO 12947-2-1998, Martindale Wear & Abrasion Tester, 12 kPa Total Weight) :

Sample(A)

(I) Resistance

Face Side

70000 Rubs*

Remark : The Above Result Is The Average Of Four Test Specimens.
In Contrary To The Requirement Of The Standard To Report Individual Test Data Herein, Such
Data Will Be Available Upon Request.

* = The End Point Was Reached When 3 Yarns Broken

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.