



Received: 12/13/2017	Completed: 12/20/2017	Letter: II	RV	P.O.#:	Test Report #: 3-23643-1-
Client's Identification	Style: Breeze Fusion. Composition: 88% Wool of New Zealand, 12% Polyamide. Weight: 590 g/lm. Product End Use: Upholstery. Color #: 4003/G.Beige				
Tested For: Bente Ellingsoe, Quality Department			Key Test: AATCC 8 or 116 Crocking/ACT		95
Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125		Ext:

Test Category: Crocking Specifier: ACT NTR 4/16 PC: 4H LE 2015; V 08/15 /dl SM/mg

TEST PERFORMED:

- AATCC Test Method 8 - Colorfastness to Crocking: AATCC Crockmeter Method, as specified for certain products
- AATCC Test Method 116 - Colorfastness to Crocking: Rotary Vertical Crockmeter Method, as specified for drapery prints

As cited by the ACT Voluntary Performance Guidelines (January 2015)  
 Evaluated by comparison with AATCC Chromatic Transference Scale

ACCEPTANCE CRITERIA

PRODUCT CATEGORY:	DRY:	WET:
<input checked="" type="checkbox"/> Upholstery	Grade 4 minimum	Grade 3 minimum
<input type="checkbox"/> Direct Glue Wallcoverings	Grade 3 minimum	Grade 3 minimum
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	Grade 3 minimum	Grade 3 minimum
<input type="checkbox"/> Drapery (solid)	Grade 3 minimum	Grade 3 minimum
<input type="checkbox"/> Drapery (print)	Grade 3 minimum	Grade 3 minimum

RESULTS: Color Transfer to Transfer Cloth

Rating

Dry: Grade 4.5  
 Wet: Grade 4.5

- RATING SYSTEM:
- Grade 5 - No color transfer
  - Grade 4 - Slight color transfer
  - Grade 3 - Moderate color transfer
  - Grade 2 - Considerable color transfer
  - Grade 1 - Excessive color transfer

CONCLUSION: Based on the reported Results and cited Acceptance Criteria, the item tested:

Complies;  Does not comply

REMARKS: None.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

\_\_\_\_\_  
 AUTHORIZED SIGNATURE

Phyllis Pettit

JAN 05 2018

GOVMARK

(Page 1 of 1)

/jb  
 lpm