



Test
TS EN ISO/IEC 17025
AB-0342-T

AB-0342-T

144420356

08/25

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

Page 1 of 5

Test Report

GABRIEL A/S

Hjulmagervej 55, DK-9000 Aalborg

Report No. 144420356
Buyer /
Test Item. : UMI col.61322
Design No. : 230861322
Manufacturer : /
Fiber Content. : /
Colour Name. : Light Beige
Order No. : 0011822780
Test Scope : Customer Selected Parameters

**Applicant's Provided
Care Instruction/Label:** -

Sample Receiving date: 2025-06-20(p.m)

Testing Period: 2025-06-23 to 2025-08-04

Report Date: 2025-08-04

Test Result: Pass

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş. accredited by TÜRKAK under registration number AB-0342-T for ISO/IEC 17025-2017 as test laboratory

The Turkish Accreditation Agency (TÜRKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of the test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following, pages which are part of this report

For and on behalf of
TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Elif Kocasalli / CR Assistant
Project Manager

Kivanc Karatas / Chemical
Laboratory Manager

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

The results given in this report belong to the received sample by vendor.

This test report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

This test report is signed by digital signature.

TÜV Rheinland testing laboratories apply the Zero Guard band rule for statement of conformity evaluation, unless other decision rule is required by the customer.

AB-0342-T
144420356
08/25

Test Result Summary :

Test Specification:


- 1 Abrasion Resistance - Determination Of Specimen Breakdown
- 2 Seam Slippage

Test result:

PASS

NO COMMENT

1. Photo



2. List of Materials

Material List:

Material No.	Material	Color	Location
M001	Textile	Light Beige	Woven base (Umi col.61322)

AB-0342-T
144420356
08/25

1.Abrasion Resistance - Determination Of Specimen Breakdown

Test method : Abrasion Resistance - Determination Of Specimen Breakdown

Load : 12kPa
70.000 rubsM001Requirement

Shade Change @ rubs >70.000

>70.000

AB-0342-T
144420356
08/25

2.Seam Slippage

Test method : Seam Slippage (BS/DIN/EN/ISO 13936-2)

180 N

M001RequirementSO 5N from 180 N

// to warp 3.2 mm

// to weft 2.9 mm

-

-

-

Remark : SO 5N = Seam opening at 5N
FTS = Fabric torn at seam
STB = Sewing thread broken
FR = Fabric ruptured
* = Seam ruptured below 60 / 120 / 180 N

- END -