



**For the Account of** Gabriel A/S  
Hjulgagervej 55  
9000 Aalborg Denmark

**Client's Identification** Arch Mesh col.70008

## CERTIFICATE OF TESTING

**TEST PERFORMED** Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-21(G-E)

### TEST RESULTS

Specimen	Breaking Force (lbf)
1	196
2	186
3	180
4	183
5	185
Avg. Warp	186

  

	Breaking Force (lbf)
1	263
2	248
3	269
4	266
5	266
6	257
7	245
8	255
Avg. Fill	259

### NOTES

**Test Conditions** 70 ±4°F, 65 ±5% Relative Humidity  
**Sampling Method** As Received  
**Equipment Used** Tinius Olson H5KT Universal Testing Machine  
**Load Cell Maximum** 1000 pounds  
**Jaw Size** 1 inch x 1 inch (face and back), rubber coated  
**Samples Tested** Conditioned After Wetting

### ACCEPTANCE CRITERIA

#### ACT Performance Guideline Criteria

**Woven + Knitted**  
Upholstery, *Indoor + Outdoor* 50 pounds minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 12/22/2025