



The  
**Govmark**  
Organization, Inc.

96D Allen Blvd.,  
Farmingdale NY 11735  
TEL: (516)293-8944  
FAX: (516)293-8956  
Page 1

|                    |                     |            |    |        |                             |
|--------------------|---------------------|------------|----|--------|-----------------------------|
| Received: 06/08/98 | Completed: 06/29/98 | Letter: H1 | jd | P.O.#: | Test Report #: 2-20219-0-01 |
|--------------------|---------------------|------------|----|--------|-----------------------------|

|                         |                                          |
|-------------------------|------------------------------------------|
| Client's Identification | Ultraleather HP (Style 291). Color 3609. |
|-------------------------|------------------------------------------|

|                                             |                       |      |
|---------------------------------------------|-----------------------|------|
| Tested For: <b>Danielle Boecker Primack</b> | Key Test: ASTM D 5034 | 65   |
| Springs Industries                          |                       |      |
| 104 W 40 Street                             | Tel: 1-(212)-556-6553 | Ext: |
| New York, NY 10018                          | Fax: 1-(212)-556-6520 |      |

TEST PERFORMED:

ASTM D 5034 (previously ASTM D 1682)

Standard Test Method for Breaking Force of Textile Fabrics (Grab Test)

| RESULTS:   | Machine<br>Direction<br>(lbs) | Cross Machine<br>Direction<br>(lbs) |
|------------|-------------------------------|-------------------------------------|
| Specimen # |                               |                                     |
| 1          | 95                            | 102                                 |
| 2          | 98                            | 92                                  |
| 3          | 88                            | 95                                  |
| 4          | 93                            | 90                                  |
| 5          | 93                            | 97                                  |
| Avg        | 93                            | 95                                  |

REMARKS:

None.

CERTIFICATION:

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM D 5034.

\_\_\_\_\_  
SIGNATURE OF LABORATORY SUPERVISOR  
THE GOVMARK ORGANIZATION, INC.

jd