



Confidential Report

Our Ref: 23/60801D-Supp/03/23





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 May 2023

Our Ref: 23/60801D/03/23

Your Ref: ---

Page: 1 of 4

Client: Gabriel A/S

Hjulgagerve 55
DK-900 Aalborg
Denmark

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 20 March 2023

Date Test Started: 29 March 2023

Description of Sample: One sample of fabric, which was referenced by the client as;
Nobel 61290I

Work Requested: We were asked to make the following fire test:

BS 5852: Clause 11:2006 (2011)

This is a supplementary report to the one issued on the 29th of March 2023 under our report reference 23/60801d.

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the items tested.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 May 2023

Our Ref: 23/60801D/03/23
Your Ref: ---

Page: 2 of 4

Client: Gabriel A/S

Testing BS 5852: Clause 11: 2006 (2011) Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources – Source 5 (Crib 5)

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The sample was conditioned in the environments specified in Clause 10 of BS 5852: 2006 (2011).

Testing

The material was tested according to BS 5852:2006 (2011) Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5).

The sample was tested at 18°C and 61% relative humidity (R.H.).

The sample was tested over combustion modified polyurethane foam with a density of approximately 49-51kg/m³.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 12 May 2023

Our Ref: 23/60801D/03/23
 Your Ref: ---

Page: 3 of 4

Client: Gabriel A/S

Results

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Specimen 1	Specimen 2
Time of Ignition (s)	44	58
Time of Flame Extinction (s)	584	309
Time of Smoke Extinction (s)	628	365
Time of cover split	61	83
Extent of damage (mm) - Seat		
Width	184	128
Length	143	102
Depth	62	53
Extent of damage (mm) - Back		
Width	236	148
Depth	70	66
Melting	Yes	No
Dripping	No	No
Charring	Yes	Yes
Comments and Observations		
Specimen Result (Ignition or Non-ignition)	Non-Ignition	Non-Ignition

Acronyms

ME – Manually extinguished
 DNO – Did not observe time of events

EC – Escalating combustion
 BTT – Burnt through thickness of foam

DNS – Material did not split
 BTE – Burnt to extremities



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
 A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
 BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
 The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
 Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 May 2023

Our Ref: 23/60801D/03/23

Your Ref: ---

Page: 4 of 4

Client: **Gabriel A/S**

Comment

The results indicate 'Non-Ignition' of the materials and the test is designated NI/5 (ie. Pass).


Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Uncertainty Budget

Measurements: ± 2 mm

Timings: ± 2 seconds

Reported by:  B Bland, Technical Customer Services Officer

Countersigned by:  P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.