



Date of Issue: 6/9/2025
Report Number: 25-001545
Revision Number:1
Date Order Received: 06/03/2025

For the Account of: Gabriel A/S
Hjulgagervej 55
9000 Aalborg Denmark

Client's Identification: FOCUS MELANGE

CERTIFICATE OF TESTING

TEST PERFORMED: Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textile
Fabrics: Martindale Tester ASTM D4970/D4970M-22

TEST RESULTS

| Specimen | Rating |
|----------|--------|
| 1 | 3.0 |
| 2 | 3.0 |
| 3 | 2.5 |
| 4 | 2.5 |
| Average | 3.0 |

RATING SYSTEM

| | |
|-----------|---------------------|
| Class 5.0 | No Pilling |
| Class 4.0 | Slight Pilling |
| Class 3.0 | Moderate Pilling |
| Class 2.0 | Severe Pilling |
| Class 1.0 | Very Severe Pilling |

NOTES

| | |
|---------------------------|---|
| Test Conditions: | 70 ±4°F, 65 ±5% Relative Humidity |
| Sampling Method: | As Received |
| Viewing Apparatus: | SpectraLight QC Lightbooth |
| Viewing Option: | 45 degree |
| Rating Standard: | ADJD3512 Photographic Standards |
| Running Times: | 1000 movements |
| Material Tested: | As Received (no refurbishment), unless otherwise noted in Client Identification above |

ACCEPTANCE CRITERIA

| | |
|-------------------------|----------------------------|
| A.C.T. Standard: | Acceptance Criteria |
| Upholstery | Class 3 minimum |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 06/06/2025