



For the Account of Gabriel A/S
Hjulgagervej 55
9000 Aalborg Denmark

Client's Identification CORE col. 70999

CERTIFICATE OF TESTING

TEST PERFORMED Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-21(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)
1	177
2	190
3	186
4	192
5	196
Avg. Warp	188

	Breaking Force (lbf)
1	214
2	191
3	211
4	219
5	209
6	210
7	211
8	218
Avg. Fill	210

NOTES

Test Conditions 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method As Received
Equipment Used Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum 1000 pounds
Jaw Size 1 inch x 1 inch (face and back), rubber coated
Samples Tested Conditioned After Wetting

ACCEPTANCE CRITERIA

ACT Performance Guideline Criteria

Woven + Knitted
Upholstery, *Indoor + Outdoor* 50 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 11/24/2025