



Date of Issue: 4/25/2025
Report Number: 25-001107
Revision Number: 1
Date Order Received: 04/15/2025

For the Account of: Gabriel A/S
Hjulmagervej 55
9000 Aalborg Denmark

Client's Identification: UMI col.64289 LIGHT RED

CERTIFICATE OF TESTING

TEST PERFORMED: Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D 5034-21(G-E)

TEST RESULTS

Specimen	Breaking Force (lbf)
1	152
2	163
3	155
4	163
5	154
Avg. Warp	157

	Breaking Force (lbf)
1	182
2	198
3	187
4	181
5	188
6	172
7	186
8	181
Avg. Fill	184

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Sampling Method: As Received
Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Samples Tested: ☒Conditioned ☐After Wetting

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	50 pounds minimum
Panels and Upholstered Walls	35 pounds minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Jennifer Friend

Authorized Signature

Date Order Completed: 04/25/2025