Test
TS EN ISO/IEC 17025
AB-0342-T

AB-0342-T
144446776
10/26

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

Test Report

GABRIEL A/S

Hjulmagervej, Aalborg DK-9000, Denmark

Report No.	144446776
Buyer	/
Test Item. :	Fame col.68143
Lot No. :	/
Manufacturer :	/
Fiber Content. :	/
Colour Name. :	/
Article No. :	/
End Use. :	/
Test Scope. :	Customer selected parameters.

Applicant's Provided Care Instruction/Label:	-
Sample Receiving date:	2026-08-26 p.m. (Confirmation date:2026-10-14)
Testing Period:	2026-08-28 to 2026-10-12
Report Date:	2026-10-16
Test Result:	No Comment

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş accredited by TÜRKAK under registration number AB-0342-T for ISO/IEC 17025-2017 as test laboratory

The Turkish Accreditation Agency (TÜRKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of the test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following, pages which are part of this report

For and on behalf of
TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş

Elif Kocasalli / CR Assistant Project Manager

Abdullah Akil / Physical Laboratory Manager

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

The results given in this report belong to the received sample by vendor.
This test report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.
This test report is signed by digital signature.
TÜV Rheinland testing laboratories apply the Zero Guard band rule for statement of conformity evaluation, unless other decision rule is required by the customer.

Test Result Summary :

Test Specification:	*Test result:*
1 Pilling Resistance - Modified Martindale Method	NO COMMENT

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

1. Photo



2. List of Materials

Material List:

Material No.	Material	Color	Location
M001	Textile	Dark Green	Woven base (Fame col.68143)

1.Pilling Resistance - Modified Martindale Method

Test method : Pilling Resistance - Modified Martindale Method (BS/DIN/EN/ISO 12945-2:2020)

415g 2.000 rubs

	M001			Requirement
	Pilling	Fuzzing	Matting	
After 2000 revs	4-5	4-5	4-5	-
Average	4-5	4-5	4-5	-

415g 5.000 rubs

	M001			Requirement
	Pilling	Fuzzing	Matting	
After 5000 revs	4-5	4-5	4-5	-
Average	4-5	4-5	4-5	-

Remark : NA=Not Applicable

- END -