

## Gabriel internal test report for bleach cleanability

<b>Test performed:</b>	12 July 2024
<b>Test:</b>	BIFMA HCF 8.1-2019 Health Care Furniture design guidelines or cleanability & ACT Test Method 1-2020
<b>Bleach concentration:</b>	1:10 Sodium Hypochlorite 5.25 – 6.25 %
<b>Product tested:</b>	2490 Tonal – 100 % post-consumer recycled polyester

Gabriel tests all polyester fabrics, and tests include all colour options for each fabric. Tests are conducted in accordance with BIFMA's and ACT's recommended cleanability guidelines for use of cleaners, sanitisers and disinfectants on fabrics in hospitals and health care settings. The test result for each colour includes an assessment of the risk for colour change, when bleach is applied to the fabric in the concentrations required in health care environments.

When choosing a bleach-cleanable product, it is important to be aware that a variety of test methods to evaluate bleach resistance exist. Consequently, we recommend that you always ensure that the test method applied to a specific fabric meets the requirements - in terms of bleach concentration, application and contact time - for the specific context and environment in which the fabric will be used.

The test method applied by Gabriel is extremely thorough, and we consider it to be the best test available to assess and inform about the risk for colour change when using chlorine products.

### Test description

1 ml of hospital grade disinfectant cleaner - diluted in accordance with the manufacturer's instructions - is applied to the centre of the test specimen. The solution is allowed to set for a period of two hours, after which any remaining liquids are blotted up (on both face and back).

The process is repeated for a total of ten times. Two hours after the 10<sup>th</sup> application, three ml of water are applied, excess fluids are blotted up with a clean white cloth, and the test specimen is allowed to air dry. The last step is repeated if chemical residue remains.

The material is evaluated by comparing the test specimen with AATCC Grey Scale for Color change.

### Rating system – Grades according to AATCC Grey scale

Grade 5 – Very good-excellent

Grade 4 – Good

Grade 3 – Fair-moderate

Grade 2 – Poor behaviour

Grade 1 – Very poor

### Acceptance criteria according ACT/BIFMA.

**Colour Change:** Grade 4 minimum

**Colour Transfer:** Not permitted

**Physical damage:** Not permitted

Fabric	Colour	Name	Risk for colour changes*	Result
Tonal	66284	Light Grey-Blue	Low	4-5
Tonal	65147	Grey Purple	Low	4-5
Tonal	66245	Blue	Low	4-5
Tonal	61317	Light Beige	Low	4
Tonal	62156	Light Yellow	Medium	3-4
Tonal	63153	Light Red-Orange	Medium	3-4
Tonal	68264	Dark Green	Medium	3-4
Tonal	68325	Green	High	3
Tonal	68261	Light Yellow-Green	High	3
Tonal	68277	Dark Yellow-Green	High	2-3

\*) Low risk = Grade 4-5; Medium risk = Grade 3-4; High risk = Grade 3 and below

Gabriel A/S confirms that the above results were obtained after testing the specimen in accordance with the procedures and equipment specified above.

Gabriel A/S



Kurt Nedergaard  
Director of CSR & Quality