

Test Report	No. 28515731	Date: 27th March 2025	Page 1 of 3
--------------------	---------------------	---	--------------------

AMENDMENT TEST REPORT

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description	:	V20 Uptown col 2217 Yellow Green
Customer	:	Gabriel; Hjulmagervej 55, DK, 9000 Aalborg
Submitted by	:	Alexander Holtermann
Style Number	:	V20 Uptown col 2217 Yellow Green
Colour	:	None Given
Product type	:	Upholstery
Fiber content	:	100% rec PES

Test Performed : Selected test(s) as requested by applicant
 Sample Receiving Date : 11th March 2025
 Testing Period : 11th March 2025 – 27th March 2025
 Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Results
Abrasion Resistance	-
Pilling Resistance	-
Seam Slippage	-

Amendment to pilling resistance grades

* Sent to UK accredited UKAS Testing Centre

** Sent to in group Turkey accredited Testing Centre

Signed for and on behalf of
TÜV Rheinland UK LTD

**Christopher
Clarke**

Digitally signed by
Christopher Clarke
Date: 2025.03.31 11:43:39
+01'00'

Chris Clarke
Laboratory Supervisor



Test result is drawn according to the kind and extent of tests performed.

Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.



Test Report	No. 28515731	Date: 27th March 2025	Page 2 of 3
--------------------	---------------------	---	--------------------

Results:

Abrasion Resistance (BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)			
Result			
	Specimen 1	Specimen 2	Specimen 3
End point reached, three thread breakdown	115,000	110,000	115,000
Overall	110,000		
Colour Change At 3000 (rubs)	4-5	4-5	4-5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

Pilling Resistance (BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric) No cleansing required	
Sample	Average Result
After 2000 Rubs Rating	Fuzzing: 4-5 Pilling: 4-5 Matting: 4-5
After 5000 Rubs Rating	Fuzzing: 4 Pilling: 4-5 Matting: 4-5



TÜVRheinland®
Precisely Right.

Softlines

Gabriel®

Test Report	No. 28515731	Date: 27th March 2025	Page 3 of 3
--------------------	---------------------	---	--------------------

Seam Slippage (BS EN ISO 13936-2:2004)	
Sample	Result
Warp	1.2 mm
Weft	1.2 mm

-End of Test Report-