


Confidential Report

Our Ref: 23/65039B/09/26



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 October 2026

Our Ref: 23/65039B/09/26
Your Ref: --

Client: **Gabriel A/S**

Hjulmagerve 55
DK-900 Aalborg
Denmark

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 07 September 2026

Date Test Started: 12 October 2026

Description of Sample: One sample of fabric, which was referenced by the client as;

Athlon Plus col.66140

Work Requested: We were asked to test the received sample to the following standard:

BS EN 1021: Parts 1 & 2:2014 – Ignitability of Upholstered Furniture

* subcontracted test, UKAS accredited
** subcontracted test, EN ISO/IEC 17025 accredited
*** not UKAS accredited

This report relates only to the items tested.
All tests were carried out in the laboratories in Leeds, unless otherwise indicated.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2026 Shirley Technologies Limited. All rights reserved.

1066

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 October 2026

Our Ref: 23/65039B/09/26
Your Ref: --

Client: **Gabriel A/S**

FIRE TEST ACCORDING TO BS EN 1021-1:2014
Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

Pre-Treatment

The material received no pre-treatment as the fabric is stated to not have an FR treatment.

Conditioning

The sample was conditioned for at least 24 hours at a temperature of 23±2°C and relative humidity of 50±5%.

The sample was tested in a room of volume 25m^3 and 19ºC.

Procedure

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material, and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 34-36 kg/m^3.

Tests were made using ignition source 0.

Requirements

The specimens shall not: -

Smouldering Criteria

a) display escalating combustion requiring active extinction.
b) smoulder or burn until it is essentially consumed within the test duration.
c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
d) smoulder for more than one hour.
e) on final examination, show evidence of progressive smouldering.

1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2026 Shirley Technologies Limited. All rights reserved.

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 October 2026

Our Ref: 23/65039B/09/26
Your Ref: --

Client: **Gabriel A/S**

Requirements (continued)

Flaming Criteria

a) show evidence of flaming initiated by a smouldering source.

Results

	Specimen No.		
Smouldering criteria	**1**	**2**	**3[1]**
Unsafe escalating combustion	No	No	No
Testing assembly consumed	No	No	No
Smoulders to extremities/full thickness	No	No	No
Smoulders more than 1 hour	No	No	No
In final examination, presence of progressive smouldering	No	No	No

Flaming criteria	**1**	**2**	**3[1]**
Occurrence of flames	No	No	No
Specimen Result Ignition (I) / Non Ignition (NI)	**NI**	**NI**	**NI**

Any “Yes” in smouldering or flaming criteria means Ignition

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.

1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2026 Shirley Technologies Limited. All rights reserved.

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 October 2026

Our Ref: 23/65039B/09/26
Your Ref: --

Client: **Gabriel A/S**

FIRE TESTS ACCORDING TO BS EN 1021-2:2014
Assessment of the ignitability of upholstered furniture. Part 2. Ignition Source 1: Match flame equivalent.

Pre-Treatment

The material received no pre-treatment as the fabric is stated to not have an FR treatment.

Conditioning

The sample was conditioned for at least 24 hours at a temperature of 23±2°C and relative humidity of 50±5%.

The sample was tested in a room of volume 25m^3 and 19ºC.

Procedure

The test was carried out in accordance with BS EN 1021-2:2014. The sponsor sampled the material, and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 34-36 kg/m^3.

Tests were made using ignition source 1.

Requirements

The specimens shall not: -

Smouldering Criteria

a) display escalating combustion requiring active extinction.
b) smoulders until it is essentially consumed within the test duration.
c) smoulder to the extremities of the specimen, or through the full thickness, within the duration of the test.
d) smoulder for more than one hour.
e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.

1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2026 Shirley Technologies Limited. All rights reserved.

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 October 2026

Our Ref: 23/65039B/09/26
Your Ref: --

Client: **Gabriel A/S**

Requirements (Continued)

Flaming Criteria

a) display escalating combustion requiring active extinction.
b) burns until it is essentially consumed within the test duration.
c) burns to the extremities of the specimen, or through the full thickness, within the duration of the test.
d) exhibit any flaming for more than 120 seconds after removal of the burner tube.

Results

	Specimen No.		
Smouldering criteria	**1**	**2**	**3**
Unsafe escalating combustion	No	No	No
Testing assembly consumed	No	No	No
Smoulders to extremities/full thickness	No	No	No
Smoulders more than 1 hour	No	No	No
In final examination, presence of progressive smouldering	No	No	No

Flaming criteria	**1**	**2**	**3**
Unsafe escalating combustion	No	No	No
Testing assembly consumed	No	No	No
Flames to extremities/full thickness	No	No	No
Flames longer than 120 seconds	No	No	No
Specimen Result Ignition (I) / Non Ignition (NI)	**NI**	**NI**	**NI**

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2026 Shirley Technologies Limited. All rights reserved.

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 October 2026

Our Ref: 23/65039B/09/26
Your Ref: --

Client: **Gabriel A/S**

Comments

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-2.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

Timings:	±2 seconds.
Measurements:	±2mm.

Reported by:..... B Bland, Technical Customer Service Officer

Countersigned by:..... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.

1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2026 Shirley Technologies Limited. All rights reserved.