



Test
TS EN ISO/IEC 17025
AB-0342-T

AB-0342-T

144420812

07/25

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

Page 1 of 4

Test Report

GABRIEL A/S

Hjulgagervej 55, DK-9000 Aalborg

Report No. 144420812
Buyer /
Test Item. : Just 248960118
Design No. : 248960118
Manufacturer : /
Fiber Content. : /
Colour Name. : Light Grey
Order No. : 0011823742
Test Scope : Customer Selected Parameters

Applicant's Provided -
Care Instruction/Label:

Sample Receiving date: 2025-06-27 (pm)

Testing Period: 2025-06-30 to 2025-07-28

Report Date: 2025-07-28

Test Result: No Comment

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş. accredited by TÜRKAK under registration number AB-0342-T for ISO/IEC 17025:2017 as test laboratory

The Turkish Accreditation Agency (TÜRKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of the test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following, pages which are part of this report

For and on behalf of
TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Nalan Aslantas / CR Assistant
Manager & Project Manager

Abdullah Akil / Physical
Laboratory Manager

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

The results given in this report belong to the received sample by vendor.

This test report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

This test report is signed by digital signature.

TÜV Rheinland testing laboratories apply the Zero Guard band rule for statement of conformity evaluation, unless other decision rule is required by the customer.

AB-0342-T
144420812
07/25

Test Result Summary :


Test Specification:

1 Pilling Resistance - Modified Martindale Method

Test result:

NO COMMENT

1. Photo



2. List of Materials

Material List:

Material No.	Material	Color	Location
M001	Textile	Light Grey	Woven base (Just 248960118)

AB-0342-T
144420812
07/25

1.Pilling Resistance - Modified Martindale Method

Test method : Pilling Resistance - Modified Martindale Method (BS/DIN/EN/ISO 12945-2)

415g 2.000 rubs

	<u>Pilling</u>	<u>M001 Fuzzing</u>	<u>Matting</u>	<u>Requirement</u>
After_2000_ revs				-
Test specimen 1	4-5	4-5	4-5	-
Test specimen 2	4-5	4-5	4-5	-
Test specimen 3	4-5	4-5	4-5	-
Average	4-5	4-5	4-5	-

415g 5.000 rubs

	<u>Pilling</u>	<u>M001 Fuzzing</u>	<u>Matting</u>	<u>Requirement</u>
After_5000_ revs				-
Test specimen 1	4-5	4-5	4-5	-
Test specimen 2	4-5	4-5	4-5	-
Test specimen 3	4-5	4-5	4-5	-
Average	4-5	4-5	4-5	-

Remark : NA=Not Applicable

- END -