



Date of Issue: 1/5/2024  
 Report Number: 23-003915  
 Revision Number:1  
 Date Order Received: 12/27/2023

For the Account of: Gabriel A/S  
 Hjulmagervej 55  
 9000 Aalborg Denmark

Client's Identification: Tailor col.61305

### CERTIFICATE OF TESTING

**TEST PERFORMED:** Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Martindale Tester  
 ASTM D4970/D4970M-16e2

#### TEST RESULTS

Specimen	Rating 1.5 in	Rating 5.5 in	
1	4.0	4.5	
2	4.0	4.5	
3	4.0	4.5	
4	4.0	4.5	
<b>Average</b>	4.0	4.5	<b>Overall Average: 4.5</b>

#### RATING SYSTEM

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

#### NOTES

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling Method:** As Received
- Viewing Apparatus:** SpectraLight QC Lightbooth
- Viewing Option:** 45 degree
- Rating Standard:** ADJD3512 Photographic Standards
- Running Times:** 1000 movements

#### ACCEPTANCE CRITERIA

- A.C.T. Standard:** Upholstery
- Acceptance Criteria:** Class 3 minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*Berta Stiver*

Authorized Signature

Date Order Completed: 01/03/2024