

<b>Test Report</b>	No. 28514685a	Date: 29 <sup>th</sup> August 2024	Page 1 of 2
--------------------	---------------	------------------------------------	-------------

**AMENDMENT TEST REPORT**

The following sample(s) was/were submitted and identified on behalf of the client as:

<b>Customer</b>	:	<b>Gabriel; Hjulmagervej 55, DK, 9000 Aalborg</b>
<b>Submitted by</b>	:	Bente Ellingsoe
<b>Style Number</b>	:	Amaze Loop col.61308

Test Performed \* \* : Selected test(s) as requested by applicant \* \* \* \* \*

Sample Receiving Date : 3<sup>rd</sup> May 2024

Testing Period : 3<sup>rd</sup> May – 23<sup>rd</sup> May 2024

Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property	Results
Abrasion Resistance	-

Amendment due to the omission of pilling resistance at client request

Signed for and on behalf of  
TÜV Rheinland UK LTD

**Christopher  
Clarke** Digitally signed by  
Christopher Clarke  
Date: 2024.08.29  
09:54:54 +01'00'



8400

**Chris Clarke**  
**Laboratory Supervisor**

*Test result is drawn according to the kind and extent of tests performed.  
Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

<b>Test Report</b>	No. 28514685a	Date: 29 <sup>th</sup> August 2024	Page 2 of 2
--------------------	---------------	------------------------------------	-------------

**Results:**

<b>Abrasion Resistance</b> (BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)			
<b>Result</b>			
	<b>Specimen 1</b>	<b>Specimen 2</b>	<b>Specimen 3</b>
End point reached, three thread breakdown	115,000	115,000	115,000
Colour Change At 3000 (rubs)	5	5	5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

-End of Test Report-