



Test
TS EN ISO/IEC 17025
AB-0342-T

| |
|------------|
| AB-0342-T |
| 144420707b |
| 03/26 |

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

Test Report

GABRIEL A/S

Hjulmagervej 55, DK-9000 Aalborg

| | |
|---|--|
| Report No. | 144420707b |
| Buyer | / |
| Test Item. : | Event Screen + COL.60004 |
| Design No. : | 859960004 |
| Manufacturer : | / |
| Fiber Content. : | / |
| Colour Name. : | Light Grey |
| Order No. : | 0011823742 |
| Test Scope : | Customer Selected Parameters |
| Revision Remark-a : | Revised of test report 144420707 dated 23.07.2025, Abrasion Resistance test method and remark have been updated. The preceding report is no longer valid |
| Revision Remark-b : | Revised of test report 144420707a dated 08.08.2025, Pilling Resistance - Modified Martindale Method test year has been added. The preceding report is no longer valid. |
| Applicant's Provided Care Instruction/Label: | - |
| Sample Receiving date: | 2025-06-26 (pm) |
| Testing Period: | 2025-06-27 to 2025-07-23 |
| Report Date: | 2026-03-06 |
| Test Result: | Pass |

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

| |
|------------|
| AB-0342-T |
| 144420707b |
| 03/26 |

Page 1 of 5

Test Report

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş accredited by TÜRKAK under registration number AB-0342-T for ISO/IEC 17025-2017 as test laboratory

The Turkish Accreditation Agency (TÜRKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of the test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following, pages which are part of this report

For and on behalf of
TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş



Nalan Aslantas / CR Assistant
Manager & Project Manager



Abdullah Akil / Physical
Laboratory Manager

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

The results given in this report belong to the received sample by vendor.

This test report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

This test report is signed by digital signature.

TÜV Rheinland testing laboratories apply the Zero Guard band rule for statement of conformity evaluation, unless other decision rule is required by the customer.

Products

| |
|------------|
| AB-0342-T |
| 144420707b |
| 03/26 |

Test Result Summary :

Test Specification:

- 1 Abrasion Resistance - Determination Of Specimen Breakdown
- 2 Pilling Resistance - Modified Martindale Method

Test result:

PASS
NO COMMENT

| |
|------------|
| AB-0342-T |
| 144420707b |
| 03/26 |

1. Photo



2. List of Materials

Material List:

| Material No. | Material | Color | Location |
|--------------|----------|-------|---------------------------------------|
| M001 | Textile | Grey | Woven base (Event Screen + col.60004) |

| |
|------------|
| AB-0342-T |
| 144420707b |
| 03/26 |

1.Abrasion Resistance - Determination Of Specimen Breakdown

Test method : Abrasion Resistance - Determination Of Specimen Breakdown (EN ISO 12947-2: 2016 / AC: 2006 acc. to EN ISO 14465: 12kPa Martindale)

Load : 12kPa
80.000 rubs

| | <u>M001</u> | <u>Requirement</u> |
|---------------------|-------------|--------------------|
| Abrasion Resistance | >80.000 | >80.000 |

Remark : No 3 threads broken

| |
|------------|
| AB-0342-T |
| 144420707b |
| 03/26 |

2.Pilling Resistance - Modified Martindale Method

Test method : Pilling Resistance - Modified Martindale Method (BS/DIN/EN/ISO 12945-2:2020)

415g 2.000 rubs

| | <u>Pilling</u> | <u>M001 Fuzzing</u> | <u>Matting</u> | <u>Requirement</u> |
|------------------|----------------|-------------------------|----------------|--------------------|
| After_2000_ revs | | | | - |
| Test specimen 1 | 4-5 | 4-5 | 4-5 | - |
| Test specimen 2 | 4-5 | 4-5 | 4-5 | - |
| Test specimen 3 | 4-5 | 4-5 | 4-5 | - |
| Average | 4-5 | 4-5 | 4-5 | - |

415g 5.000 rubs

| | <u>Pilling</u> | <u>M001 Fuzzing</u> | <u>Matting</u> | <u>Requirement</u> |
|------------------|----------------|-------------------------|----------------|--------------------|
| After_5000_ revs | | | | - |
| Test specimen 1 | 4-5 | 4-5 | 4-5 | - |
| Test specimen 2 | 4-5 | 4-5 | 4-5 | - |
| Test specimen 3 | 4-5 | 4-5 | 4-5 | - |
| Average | 4-5 | 4-5 | 4-5 | - |

Remark : NA=Not Applicable

- END -